AMENDMENTS TO CLAIMS

This listing of claims will replace all prior versions, or listings, of claims in the present application.

Claims 1-7 (Cancelled).

Claim 8 (Previously Presented) A water-soluble or water-dispersible polyurethane comprising a reaction product of

A) at least one polyether a1) having an average functionality of \geq 3 and at least one urethane group-containing polyether polyol a2) having an average functionality of \geq 4,

- B) at least one C₆-C₂₂ monoalcohol,
- C) at least one (cyclo)aliphatic and/or aromatic diisocyanate
- D) a C₂-C₁₈-oxime and/or diamine with 2 to 18 carbon atoms,
- E) optionally at least one C₄-C₁₈ monoisocyanate,
- F) optionally at least one polvisocyanate havina an average functionality of>

wherein the starting NCO/OH equivalent ratio is between 0.5:1 to 1.2:1; and wherein the production of polyether alcohol mixture A) containing polyethers a1) and urethane group-containing polyethers a2) has been carried out by the partial reaction of polyethers a1) with at least one organic polyisocyanate having a functionality of ≥ 2, and wherein up to 50 mole % of polyethers are reacted with isocyanates.

Claims 9-16 (Cancelled).

Claim 17. (Previously Presented): The polyurethane of Claim 8, wherein the polyether polyol a1) has an average functionality of 3 to 4.

Mo-6800N

2;

Claim 18. (Previously Presented): The polyurethane of Claim 8, wherein the polyether polyol a1) has an average functionality of 4 to 6.

Claim 19. (Previously Presented): The polyurethane of Claim 8, wherein component B) comprises a C6-C22 monoalcoho!.

Claim 20. (Previously Presented): The polyurethane of Claim 8, wherein component B) comprises a C8-C18 monoalcohol.

Claim 21. (Previously Presented): The polyurethane of Claim 8, wherein component B) comprises a Ca-C14 monoalcohol.

Claim 22. (Previously Presented): The polyurethane of Claim 8, wherein the component C) comprises a (cyclo)aliphatic diisocyanate.

Claim 23. (Currently Amended): A process for the production of the water-soluble or water dispersible polyurethane of Claim 8, comprising reacting

A) a mixture of at least one polyether polyol a1) having a mean an average functionality of \geq 3 and at least 1 urethane group-containing polyether polyol a2) having an average functionality of \geq 4, wherein production of polyether polyol mixture A) containing polyethers a1) and urethane group-containing polyethers a2) has been carried out by the partial reaction of polyethers a1) with at least one organic polyisocyanate having a functionality of \geq 2, and wherein up to 50 mole % of polyethers are reacted with isocyanates.

- B) at least one C₆-C₂₂ monoalcohol,
- C) at least one (cyclo)aliphatic and/or aromatic diisocyanate,
- D) a C₂-C₁₈ oxime and/or diamine with 2 to 18 carbon atoms,
- E) optionally at least one C4-C18 monoisocyanate, and

Mo-6800N

wherein at a starting NCO/OH equivalent ratio-of is about 0.5:1 to about 1.2:1.

Claim 24. (Previously Presented): The process of Claim 23, wherein the urethane group-containing polyether polyol a2) comprises the reaction product of the polyether polyol a1) with a diisocyanate.

Claim 25. (Previously Presented): The process of one of Claims 23 and 24, wherein the urethane group-containing polyether polyol a2) comprises the reaction product of the polyether polyol a1) with polyisocyanates having an average functionality of 2.

Claim 26. (Currently Amended): A process for adjusting the flow properties of an aqueous paint system, adhesive and another aqueous formulation comprising adding the polyurethane <u>produced by reacting</u>; of Claim 8 thereto

A) a mixture of at least one polyether polyol a1) having an average functionality of ≥ 3 and at least 1 urethane group-containing polyether polyol a2) having an average functionality of ≥ 4 , wherein production of polyether polyol mixture A) containing polyethers a1) and urethane group-containing polyethers a2) has been carried out by the partial reaction of polyethers a1) with at least one organic polyisocyanate having a functionality of ≥ 2 , and wherein up to 50 mole % of polyethers are reacted with isocyanates.

- B) at least one C₆-C₂₂ monoalcohol.
- C) at least one (cyclo)aliphatic and/or aromatic diisocyanate,
- D) a C2-C18 oxime and/or diamine with 2 to 18 carbon atoms,
- E) optionally at least one C4-C18 monoisocyanate, and
- poptionally at least one polyisocyanate having an average functionality of >

<u>2:</u>

wherein a starting NCO/OH equivalent ratio is about 0.5:1 to about 1.2:1.

Mo-6800N

Claim 27. (Previously Presented): An aqueous paint system, adhesive and another aqueous formulation comprising the polyurethane of Claim 8.

Mo-6800N